

GREY CEMENT CEM I 42.5 N

STANDARD NA 442 (2013) / CE / EN 197-1 (2011)

STRENGTH AT 28 DAYS

≥ 42.5 MPa

FINENESS

3200 - 3800 cm²/g

PACKAGING

Bulk

UPDATED

May 2026

OVERVIEW

Portland cement for high-performance concrete, designed for a wide range of structural and general construction applications. It provides reliable mechanical strength and consistent performance, making it suitable for both cast-in-place and precast concrete.

RECOMMENDED APPLICATIONS

- Reinforced and plain concrete.
- Residential, commercial and industrial buildings.
- Foundations and structural concrete.
- Precast concrete products.
- Ready-mix concrete.
- Pumped concrete.
- Bridge decks and civil engineering structures.
- Self-compacting concrete.

CHEMICAL ANALYSIS

Sulphur Trioxide (SO ₃)	< 2.5 %
Chloride content (Cl)	< 0.1 %
Magnesium Oxide (MgO)	< 1 %
Loss On Ignition (LOI)	0.5 - 1.5 %

CLINKER MINERALOGICAL COMPOSITION (BOGUE)

C ₃ S	60 ± 3 %
C ₃ A	3 - 7.5 %

PHYSICAL PROPERTIES

Normal Consistency	26 to 28 %
Initial Setting Time (minutes)	≥ 60 min
Final Setting Time (minutes)	200 to 350 min
Expansion (mm)	< 5 mm
Fineness (SSB)	3200 - 3800 cm ² /g

COMPRESSIVE STRENGTH

7 days (EN 196-1)	≥ 10 MPa
28 days (EN 196-1)	≥ 42.5 MPa

Typical average values.